

AMENDMENTS TO THE CLAIMS

The listing of claims below replaces all prior versions of claims in the application.

1. (Original): A coating material composition with a gas-barrier property
which comprises, as essential components, an ethylene-vinyl alcohol copolymer (A)
obtained by saponifying an ethylene-vinyl acetate copolymer, an inorganic layered compound
(B) and a solvent,
wherein the total amount of (A) and (B) is 1 to 30% by mass and the mass ratio (A)/(B) is
(30/70) to (50/50).

2. (Original): The coating material composition with a gas-barrier property according to
Claim 1
wherein said ethylene-vinyl alcohol copolymer (A) has an ethylene component content of
20 to 60 mole percent and a degree of saponification of a vinyl acetate component of not lower
than 95 mole percent.

3. (Original): A process for producing the coating material composition with a gas-
barrier property according to Claim 1 or 2
which comprises the step of mixing the inorganic layered compound (B) in a solution of
the ethylene-vinyl alcohol copolymer (A) and dispersing the inorganic layer compound (B) in the
above solution under a pressure of not lower than 10 MPa using a high-pressure dispersing

device.

4. (Currently Amended): A gas-barrier composite plastic film or sheet

which is obtained by coating at least one side of a plastic film or sheet made of at least one plastic selected from the group consisting of polyolefins, polyesters, polyamides and polystyrenes with the coating material composition with a gas-barrier property according to Claim 1 or 2 [[to]] at a coating weight so as to give a dry coat layer thickness of 0.1 to 100 μm .

5. (Original): A gas-barrier packaging container

which is obtained by shaping the gas-barrier composite plastic film according to Claim 4.

6. (Cancelled)

7. (Original): A gas-barrier packaging container

which is obtained by further coating a plastic container shaped in the form of a tube, tray, cup, box or bottle with the coating material composition with a gas-barrier property according to Claim 1 or 2 at a coating weight so as to give a dry coat thickness of 0.1 to 100 μm .

8. (Original): A gas-barrier packaging container

which is formed of a composite layer composed of paper and the gas-barrier composite plastic film or sheet according to Claim 4.